

TESTREPORT

KOTITI No. | 82224021100222

To | RESPILON Production s.r.o

Date In | Mar 30, 2022

Date Out | May 06, 2022

1. Client

o Address : 602 00 Brno, Prikop 843/4

2. Test Sample

o (A) : RWM 6

3. Use of Report : Quality Control

4. Test Method : ASTM G 154-16

Affirmation	Prepared by		Technical Manager	
	Name : Jeongsu Heo		Name: Jin Hyeop Jo	

KOTITI Testing & Research Institute



Contact Information for technical questions and general inquiries.

Jin Hyeop Jo T (822)3451-7324 E jh_jo@kr.kotiti-global.com Woo Hyung Choi T (822)6191-6146 E whchoi@kr.kotiti-global.com

111, Sagimakgol-ro, Jungwon-gu, Seongnam-si, Gyeonggi-do, Korea T (822)3451-7000 F (822)3451-7177 W www.kotiti-global.com

- The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products.
- Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the KOTITI Testing & Research Institute.
- The test result in this report is not related to accreditation of KS Q ISO/IEC 17025 and KOLAS.
- You can verify the authenticity by the QR code at the bottom right side of the issued report, or access <http://cs.kotiti-global.com> and enter the test report number.



5. Test Result

Test Conducted	Method	Test Result		Unit	Remark
		Face	Back		
1	UV Resistance	ASTM G154		See detail results	-

- Continue to next page -



- Test Result Details -**1. UV Resistance****1.1 Test Condition**

Test Method	Condition		Remarks
ASTM G154 Cycle No.1	Irradiance (W/m ² ·nm)	0.89	-
	Wave length(nm)	340	
	Test time (h)	300	
	Lamp type	UVA-340	
	Black Panel Temperature (°C)	UV cycle : (60 ± 3) Condensation : (50 ± 3)	UV cycle : 8 h Condensation : 4 h

1.2 Images of apparatus and sample

Caterogy	Apparatus	Sample
Image		

1.3 Test Result

Category	(A)		Unit	Remark
	Face	Back		
Images			-	X200

- End of Report -